

### CERTIFICATE

No. A/15-468783

Date 2015-01-07 Page 1/2

Rev 00

INSPECTION CERTIFICATE acc to EN 10 204 3.1

Processkontroll Items AB Box 2088

444 02 STORA HÖGA

SWEDEN

INSPECTION STAMP QA-TUBE

Customer References

Customer

order

2014-12-23

003-00991

751354

Sandvik References

Order No. Subs No. ABSMT Dispatch note

391705 583568 38257/54

ABSMT No. C.Code 300-23722 15

ITEMS

Material description

SEAMLESS STAINLESS COLD FINISHED

HYDRAULIC TUBING

Steel/material Designations

Sandvik ATST

3R60 TP316/TP316L

EN no 1.4435

Steel making process

Electric furnace

Technical requirements

ASTM A-213-13 AW, ASME SA-213-ED-10 AD-11A AW, ASTM A-269-13

NACE MR0175/ISO 15156-3:2009

PED 97/23/EC EN 10216-5 TC1

HRB MAX 80

EXTENT OF DELIVERY

It Product designation Heat Pieces Kg M Lot 048071 34050 80 61.0 480.00

02 THT-3R60-6-1 6.00 X 1.00

> Total 80 61.0 480.00

KEY TO HEAT

Heat Code Heat No.

048071 538980

TEST RESULTS

Chemical composition (weight%)

Heat C Si Mn  $\mathtt{Cr}$ Νi Mo P S

0.028 0.0080 17.22 048071 0.018 0.43 1.79 13.15 2.52

N

048071 0.034

Chemical composition, product (weight%)

Heat C Si Mn P S  $\mathtt{Cr}$ Νi Mo 1.76 0.028 0.0087 17.26 048071 0.023 0.40 13.34 2.54

N

048071 0.053

> Quality assurance - Lars-Ake Bergqvist / QA-manager MTC Service / Certificates



# CERTIFICATE

No. A/15-468783

Date

Rev 00 2015-01-07 Page 2/2

Tensile test at room temperature

Yield strength Tensile strength Elongation MPAMPa MPa % Rp0.2 Rp1.0 Rm4D Α 34050 270 307 555 58 58

#### Hardness test

Lot

Max Min HRB HRB Lot 34050 73 74

## Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E
- Leak test: Eddy current test acc to EN 10246-2, ASME SA-1016.
- Visual inspection and dimensional control.

#### **Heat Treatment:**

Solution annealed at a temperature of Min 1040° C and quenched.

### Marking:

SANDVIK 3R60 ASTM/ASME A/SA-213 A-269 EN 10216-5 TC1 EN 10305-1 COLD EN 1.4435 TP316/316L CFA SMLS NDE 6.00 X 1.00 MM HT 538980 SS LOT 34050 MADE BY SANDVIK IN SWEDEN \*QA-TUBE\*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.