



CERTIFICATE

No. A/17-685109 Rev 00
Date 2017-09-15 Page 1/3

INSPECTION CERTIFICATE acc to
EN 10204 3.1

Processkontroll Items AB
Box 2088
444 02 STORA H@GA
SWEDEN

INSPECTION STAMP
QA-TUBE

Customer References		Sandvik References	
755354	Customer order 2017-09-14	Order No. 491052	Subs No. 636821 ABSMT No. C.Code 300-69079 15
003-00991	ITEMS	ABSMT Dispatch note 04133/54	

Material description SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Steel/material Designations Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
Steel making process Electric furnace	

Technical requirements
 ASTM A-213-17 AW, ASME SA-213-ED-15 AW, ASTM A-269-15A
 NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17945:2015
 PED 2014/68/EU EN 10216-5 TC1
 HRB MAX 80

EXTENT OF DELIVERY								
It	Product designation	Heat	Lot	Pieces	Kg	M		
02	THT-3R60-12-1 12.00 X 1.00	048479	94776	100	159.0	600.00		
				Total	100	159.0 600.00		
KEY TO HEAT			KEY TO LOT					
Heat Code	Heat No.		Lot Code	Lot No.				
048479	548724		94776	393573				
TEST RESULTS								
Chemical composition (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048479	0.016	0.41	1.62	0.029	0.011	17.25	13.18	2.62
	N							
048479	0.037							

Quality assurance - Lars-Åke Bergqvist / QA-manager
MTC Service / Certificates

**Chemical composition, product (weight%)**

Lot	C	Si	Mn	P	S	Cr	Ni	Mo
94776	0.020	0.42	1.63	0.029	0.007	17.39	13.22	2.65
	N							
94776	0.041							

Tensile test at room temperature

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
94776	256	290	543	70	58
	246	281	551	68	58

Hardness test

Lot	Min	Max
	HRB	HRB
94776	76	76

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 TP 316/TP 316L EN 1.4435 COLD SML NDE 12.00 X 1.00 MM **SAKNAS** HT 548724 SC LOT 393573
MADE BY SANDVIK *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.



No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.

TEST RESULTS TRANSFERRED FROM CERTIFICATE NO 00057364