

Dragprovning vid rumstemperatur

Ao	Sträckgräns		Brottgräns	Förlängning	
	MPa	MPa	MPa	%	%
92474	Rp0.2	Rp1.0	Rm	A	2"
	243	285	574	53	56
	246	294	581	54	55
	246	283	578	52	55

Hårdhetsprovning

Ao	Min	Max
	HRB	HRB
92474	74	75

Följande kontroller/provningar har utförts med tillfredställande res:

- Plattningsprov
- Vidgningsprov
- PMI-provning.
- Interkristallin korrosionsprovning enligt ASTM A-262 PR.E
- Interkristallin korrosionsprovning enligt EN ISO3651-2, Metod A.
- Täthetsprovning: Induktivprovning enl EN 10246-2, ASME SA-1016.
- Visuell inspektion och dimensionskontroll.

Värmebehandling:

Upplösningsbehandlat och släckt.

Märkning:

SANDVIK 3R60 ASTM/ASME A/SA-213AW/A-269 NFA 49-117 EN 10216-5 TC1 SS 2353-22
WNR 1.4435 TP 316/TP 316L Z2CND17-13 EN 1.4435 M S PK1 16.00 X 2.00 MM HT 5229
37 SZ LOT 4843543/1-1 DIN 2391 *QA-TUBE*

Godkänd enligt AD 2000-Merkblatt W0 och certifierad enligt tryckkärlsdirektivet, Pressure Equipment Directive(97/23/EG) av TUEV NORD GmbH; anmält organ, reg.no. 0045.

Antalet prover är baserat på AO-storlek före ev.delning.

De levererade produkterna uppfyller specifikationer och krav i ordern.

Materialet är tillverkat enligt ett kvalitetssystem, godkänt och certifierat mot ISO 9001.

Intyget är ADB-framställt och giltigt utan underskrift.

PROVNINGSRESULTATEN ÖVERFÖRDA FRÅN CERTIFIKAT NR A091135



CERTIFICATE

No. A/09-918932 Rev 00
Date 2009-11-24 Page 1/2

INSPECTION CERTIFICATE acc to
EN 10 204 3.1

Processkontroll Items AB
Box 2088
444 02 STORA HÖGA
SWEDEN

INSPECTION STAMP
QA-TUBE

Customer References		Sandvik References	
708027	Customer order 2009-11-13	Order No. 173999	Subs No. 155241
003-00991	ITEMS	ABSMT No. 300-12012	C.Code 15
		ABSMT Dispatch note 38595/54	

Material description SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Steel/material Designations Sandvik SS 3R60 2353 AISI AFNOR TP316/TP316L Z2CND17-13 W.nr DIN 1.4435 X 2 CRNIMO 18 14 3 EN no 1.4436/1.4435
Steel making process Electric furnace	

Technical requirements
 PED/23/EC, EN 10216 TC1
 SS 219711, DIN 17458 TC1, NFA 49-117-09/85
 ASTM A-213-08 AW, ASME SA-213-ED-07 AD-08 AW, ASTM A-269-08
 NACE MR0175/ISO 15156-3:2003, HRB Max 80

EXTENT OF DELIVERY

It	Product designation	Heat	Lot	Pieces	Kg	M
01	THT-3R60-16-2 16.00 X 2.00	047312	92474	25	106.0	150.00
				Total	25	106.0 150.00

KEY TO HEAT		KEY TO LOT	
Heat Code	Heat No.	Lot Code	Lot No.
047312	522937	92474	4843543/1-1

TEST RESULTS

Chemical composition (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
047312	0.024	0.39	1.76	0.029	0.010	17.44	13.06	2.52
	N							
047312	0.038							

Chemical composition, product (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
047312	0.022	0.41	1.77	0.029	0.012	17.40	13.11	2.53
	N							
047312	0.038							

Quality assurance - Per Eriksson/ QA-manager Tube & Pipe
MTC Service / Certificates

**Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
92474	243	285	574	53	56
	246	294	581	54	55
	246	283	578	52	55

Hardness test

Lot	Min	Max
	HRB	HRB
92474	74	75

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E
- Intergranular corrosion test acc. to EN ISO3651-2, Method A.
- Leak test: Eddy current test acc to EN 10246-2, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed and quenched.

Marking:

SANDVIK 3R60 ASTM/ASME A/SA-213AW/A-269 NFA 49-117 EN 10216-5 TC1 SS 2353-22
WNR 1.4435 TP 316/TP 316L Z2CND17-13 EN 1.4435 M S PK1 16.00 X 2.00 MM HT 5229
37 SZ LOT 4843543/1-1 DIN 2391 *QA-TUBE*

Approved acc. AD 2000-Merkblatt W0 and certified acc. to
Pressure Equipment Directive (97/23/EC) by
TUEV NORD GmbH; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot
before cutting to finished lengths.

The delivered products comply with the specifications and
requirements of the order.

The material is manufactured according to a Quality system,
approved and registered to ISO 9001.

The certificate is produced with EDP and valid without signature.

TEST RESULTS TRANSFERRED FROM CERTIFICATE NO A091135