

# CERTIFICATE

No. A/15-532803

Date 2015-10-23 Page 1/2

Rev 00

INSPECTION CERTIFICATE acc to EN 10 204 3.1

Processkontroll Items AB Box 2088

444 02 STORA HÖGA

SWEDEN

INSPECTION STAMP QA-TUBE

Customer References

Customer

order

2015-10-23

1 -----

Sandvik References

Order No. Subs No. ABSMT Dispatch note

421059 598969 07628/54

ABSMT No. C.Code 300-37265 15

003-00991 ITEMS

752523

Material description | Steel/material Designations

SEAMLESS STAINLESS COLD FINISHED | Sandvik AISI

HYDRAULIC TUBING 3R60 TP316/TP316L

EN no 1.4435

Steel making process

Electric furnace

Technical requirements

ASTM A-213-15A AW, ASME SA-213-ED-13 AW, ASTM A-269-13

NACE MR0175/ISO 15156-3:2009 PED 97/23/EC EN 10216-5 TC1

HRB MAX 80

EXTENT OF DELIVERY

 It Product designation
 Heat
 Lot
 Pieces
 Kg
 M

 01 THT-3R60-8-1
 048053 47175
 15
 16.0
 90.00

01 THT-3R60-8-1 048053 47175 15 8.00 X 1.00

Total 15 16.0 90.00

KEY TO HEAT

Heat Code Heat No.

048053 537459

TEST RESULTS

Chemical composition (weight%)

Heat C Si Mn P S Cr Ni Mo

048053 0.017 0.40 1.63 0.030 0.008 17.27 13.06 2.53

N

048053 0.044

Chemical composition, product (weight%)

Heat C Si Mn P S  $\mathtt{Cr}$ Νi Mo 0.39 0.028 0.0104 17.38 048053 0.020 1.66 13.15 2.55

N

048053 0.047

Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates



## CERTIFICATE

No. A/15-532803

Date

Rev 00 2015-10-23 Page 2/2

Tensile test at room temperature

Yield strength Tensile strength Elongation MPa MPAMPa % Rp0.2 Rp1.0 Rm4D Lot Α 47175 282 320 559 59 57

#### Hardness test

Max Min HRB HRB Lot 47175 74 76

### Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E
- Leak test: Eddy current test acc to EN 10246-2, ASME SA-1016.
- Visual inspection and dimensional control.

#### **Heat Treatment:**

Solution annealed at a temperature of Min 1040° C and quenched.

### Marking:

SANDVIK 3R60 ASTM/ASME A/SA-213 A-269 EN 10216-5 TC1 EN 10305-1 COLD AW EN 1.4 435 TP316/316L CFA SMLS NDE 8.00 X 1.00 MM HT 537459 SS LOT 47175 MADE BY SAND VIK IN SWEDEN \*QA-TUBE\*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.