CERTIFICATE



Mo

2.53

INSPECTION CERTIFICATE acc to EN 10 204 3.1

Processkontroll Items AB Box 2088 444 02 STORA HÖGA SWEDEN

INSPECTION STAMP QA-TUBE

Customer References Customer			Sandvik References Order No. Subs No. ABSMT Dispatch note				
751782	order	40	)3450	589873			
	2015-04-			C.Code			
003-00991 ITEM	C	30	0-29045	5 15			
	5						
Material description			Steel/material Designations				
SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING		11	Sandvik AISI 3R60 TP316/TP316L				
HIDRAULIC TUBING			EN no				
		1.	4435				
Steel making pr							
Electric furnac	e						
Technical requi	rements						
ASTM A-213-13 AW, ASME SA-213-ED-13 AW, ASTM A-269-13							
NACE MR0175/ISO PED 97/23/EC EN							
HRB MAX 80	10210 5 101						
EXTENT OF DELIV		Hoat	Lot	Pieces	Ka	м	
01 THT-3R6			5 41067		-		
10.00 X	1.00						
			Total	17	24 0	102.00	
KEY TO HEAT			IUCAI	± /	21.0	102.00	
	Heat No.						
048115	540236						

TEST RESULTS Chemical composition (weight%) Heat C Si Mn Р S Cr Ni 048115 1.63 0.031 0.0080 17.21 0.022 0.35 13.00 N 048115 0.041

## Chemical composition, product (weight%) Heat С Si Mn P S Cr Ni Mo 0.030 0.0060 17.28 048115 0.026 0.36 1.63 13.00 2.54 Ν 048115 0.040

Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates

AB SANDVIK MATERIALS TECHNOLOGY Reg No. 556234-6832 VAT No. SE663000-060901 SE-81181 SANDVIKEN SWEDEN www.smt.sandvik.com mtc\_service.smt@sandvik.com



Tensile test	Yield s	temperature trength MPa	Tensile strength MPa	Elongati %%%						
<b>Lot</b> 41067	<b>Rp0.2</b> 328	Rp1.0	<b>Rm</b> 579	<b>A 4D</b> 49 44	i de la companya de l					
Hardness test										
<b>Lot</b> 41067	<b>Min</b> <b>HRB</b> 75	<b>Max</b> HRB 76								
<pre>Following controls/tests have been satisfactorily performed: Flattening test. Flaring test PMI-test. Intergranular corrosion test acc to ASTM A-262 PR.E Leak test: Eddy current test acc to EN 10246-2, ASME SA-1016. Visual inspection and dimensional control.</pre>										
Heat Treatment: Solution annealed at a temperature of Min 1040° C and quenched.										
Marking: SANDVIK 3R60 ASTM/ASME A/SA-213 A-269 EN 10216-5 TC1 EN 10305-1 COLD AW EN 1.4 435 TP316/316L CFA SMLS NDE 10.00 X 1.00 MM HT 540236 SS LOT 41067 MADE BY SAN DVIK IN SWEDEN *QA-TUBE*										
The raw material is free from radioactive contamination.										
Material free from mercury contamination.										
Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.										
The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.										
The delivered products comply with the specifications and requirements of the order.										
The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.										
No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law. The certificate is produced with EDP and valid without signature.										
The certifica	ate is pr	oduced with	EDP and valid withou	ıt signatu	re.					