

INSPECTION CERTIFICATE acc to EN 10 204 3.1

Processkontroll Items AB Box 2088 444 02 STORA HÖGA SWEDEN

INSPECTION STAMP QA-TUBE

Ν

Chemical composition, product (weight%) Heat C Si Mn P

048115 0.041

048115 0.026

Customer References		Sandvik I	References				
	Customer			ABSMT Di	spatch note		
752021	order		592576	48947/54			
	2015-06-16		. C.Code				
		300-3139					
003-00991 ITEMS							
Material description	Steel/material Designations						
SEAMLESS STAINLESS COLD	FINISHED	Sandvik		AISI			
HYDRAULIC TUBING		3R60		TP316/1	TP316L		
		EN no					
		1.4435					
Steel making process							
Electric furnace							
Technical requirements							
ASTM A-213-13 AW, ASME SA-213-ED-13 AW, ASTM A-269-13							
NACE MR0175/ISO 15156-3:2009							
PED 97/23/EC EN 10216-5 TC1							
HRB MAX 80							
EXTENT OF DELIVERY		t Tat	Dieses	77			
It Product designa 01 THT-3R60-6-1		at Lot 3115 40477		Kg 23.0	M 180.00		
6.00×1.00	040	5115 40477	30	23.0	100.00		
0.00 X 1.00							
		Total	30	23.0	180.00		
KEY TO HEAT		IUCAL	50	20.0	T00.00		
Heat Code Heat No.							
048115 540236							
TEST RESULTS							
Chemical composition (we	ight%)						
Heat C Si	Mn	P	s c	r N	Ji Mo		
048115 0.022 0.35	1.63		0.0080 17.	-			

Ν 048115 0.040

Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates

AB SANDVIK MATERIALS TECHNOLOGY Reg No. 556234-6832 VAT No. SE663000-060901 SE-81181 SANDVIKEN SWEDEN www.smt.sandvik.com mtc_service.smt@sandvik.com

S

0.36 1.63 0.030 0.0060 17.28 13.00

Cr

Ni

Mo

2.54



[
Tensile test	Yield s	temperature trength MPa	Tensile strength MPa	Elon %	gation %			
Lot 40477	Rp0.2 299	Rp1.0	Rm 580	A 54	4D			
Hardness test Min Max								
Lot 40477	HRB 72	Max HRB 74						
<pre>Following controls/tests have been satisfactorily performed: Flattening test. Flaring test PMI-test. Intergranular corrosion test acc to ASTM A-262 PR.E Leak test: Eddy current test acc to EN 10246-2, ASME SA-1016. Visual inspection and dimensional control.</pre>								
Heat Treatment: Solution annealed at a temperature of Min 1040° C and quenched.								
Marking: SANDVIK 3R60 ASTM/ASME A/SA-213 A-269 EN 10216-5 TC1 EN 10305-1 COLD AW EN 1.4 435 TP316/316L CFA SMLS NDE 6.00 X 1.00 MM HT 540236 SS LOT 40477 MADE BY SAND VIK IN SWEDEN *QA-TUBE*								
The raw material is free from radioactive contamination.								
Material free from mercury contamination.								
Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.								
The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.								
The delivered products comply with the specifications and requirements of the order.								
The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.								
No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.								
The certificate is produced with EDP and valid without signature.								