

**CERTIFICATE****No. A/15-496593 Rev 00**
Date 2015-04-29 Page 1/2INSPECTION CERTIFICATE acc to
EN 10 204 3.1Processkontroll Items AB
Box 2088
444 02 STORA HÖGA
SWEDENINSPECTION STAMP
QA-TUBE

Customer References 751803 003-00991 ITEMS Customer order 2015-04-28		Sandvik References Order No. Subs No. ABSMT Dispatch note 403781 590071 45948/54 ABSMT No. C.Code 300-29238 15																																																																									
Material description SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING Steel making process Electric furnace		Steel/material Designations Sandvik AISI 3R60 TP316/TP316L EN no 1.4435																																																																									
Technical requirements ASTM A-213-13 AW, ASME SA-213-ED-13 AW, ASTM A-269-13 NACE MR0175/ISO 15156-3:2009 PED 97/23/EC EN 10216-5 TC1 HRB MAX 80																																																																											
EXTENT OF DELIVERY <table><thead><tr><th>It</th><th>Product designation</th><th>Heat</th><th>Lot</th><th>Pieces</th><th>Kg</th><th>M</th></tr></thead><tbody><tr><td>01</td><td>THT-3R60-8-1 8.00 X 1.00</td><td>048108</td><td>41444</td><td>35</td><td>37.0</td><td>210.00</td></tr><tr><td colspan="4">Total</td><td>35</td><td>37.0</td><td>210.00</td></tr></tbody></table>				It	Product designation	Heat	Lot	Pieces	Kg	M	01	THT-3R60-8-1 8.00 X 1.00	048108	41444	35	37.0	210.00	Total				35	37.0	210.00																																																			
It	Product designation	Heat	Lot	Pieces	Kg	M																																																																					
01	THT-3R60-8-1 8.00 X 1.00	048108	41444	35	37.0	210.00																																																																					
Total				35	37.0	210.00																																																																					
KEY TO HEAT <table><thead><tr><th>Heat Code</th><th>Heat No.</th></tr></thead><tbody><tr><td>048108</td><td>540237</td></tr></tbody></table>				Heat Code	Heat No.	048108	540237																																																																				
Heat Code	Heat No.																																																																										
048108	540237																																																																										
TEST RESULTS Chemical composition (weight%) <table><thead><tr><th>Heat</th><th>C</th><th>Si</th><th>Mn</th><th>P</th><th>S</th><th>Cr</th><th>Ni</th><th>Mo</th></tr></thead><tbody><tr><td>048108</td><td>0.019</td><td>0.37</td><td>1.63</td><td>0.030</td><td>0.0080</td><td>17.08</td><td>13.06</td><td>2.54</td></tr><tr><td colspan="2">N</td><td colspan="7"></td></tr><tr><td>048108</td><td>0.039</td><td colspan="7"></td></tr></tbody></table> Chemical composition, product (weight%) <table><thead><tr><th>Heat</th><th>C</th><th>Si</th><th>Mn</th><th>P</th><th>S</th><th>Cr</th><th>Ni</th><th>Mo</th></tr></thead><tbody><tr><td>048108</td><td>0.021</td><td>0.36</td><td>1.64</td><td>0.029</td><td>0.0070</td><td>17.04</td><td>13.10</td><td>2.53</td></tr><tr><td colspan="2">N</td><td colspan="7"></td></tr><tr><td>048108</td><td>0.036</td><td colspan="7"></td></tr></tbody></table>				Heat	C	Si	Mn	P	S	Cr	Ni	Mo	048108	0.019	0.37	1.63	0.030	0.0080	17.08	13.06	2.54	N									048108	0.039								Heat	C	Si	Mn	P	S	Cr	Ni	Mo	048108	0.021	0.36	1.64	0.029	0.0070	17.04	13.10	2.53	N									048108	0.036							
Heat	C	Si	Mn	P	S	Cr	Ni	Mo																																																																			
048108	0.019	0.37	1.63	0.030	0.0080	17.08	13.06	2.54																																																																			
N																																																																											
048108	0.039																																																																										
Heat	C	Si	Mn	P	S	Cr	Ni	Mo																																																																			
048108	0.021	0.36	1.64	0.029	0.0070	17.04	13.10	2.53																																																																			
N																																																																											
048108	0.036																																																																										
Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates																																																																											

**Tensile test at room temperature**

	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
Lot	Rp0.2	Rp1.0	Rm	A	4D
41444	297	335	566	55	52

Hardness test

Lot	Min	Max
	HRB	HRB
41444	72	74

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E
- Leak test: Eddy current test acc to EN 10246-2, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM/ASME A/SA-213 A-269 EN 10216-5 TC1 EN 10305-1 COLD AW EN 1.4 435 TP316/316L CFA SMLS NDE 8.00 X 1.00 MM HT 540237 SS LOT 41444 MADE BY SANDVIK IN SWEDEN *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.