

INSPECTION CERTIFICATE acc to EN 10204 3.1

Processkontroll Items AB Box 2088 444 02 STORA HÖGA SWEDEN

INSPECTION STAMP QA-TUBE

Customer References	Sandvik References				
753578	Customer order	445899	612458	ABSMT Dispatch note 24087/54	
003-00991 ITEMS	2016-06-23	ABSMT No. 300-48730			
Material description	Steel/material Designations				
SEAMLESS STAINLESS COLD	FINISHED	Sandvik		AISI	
HYDRAULIC TUBING		3R60		TP316/TP316L	
		EN no			
		1.4435			
Steel making process					
Electric furnace					
Technical requirements					

ASTM A-213-15C AW, ASME SA-213-ED-15 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17495:2015 PED 97/23/EC EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY									
It		t designat	ion	Heat	Lot		-		1
		0-10-1.5		048250	57382	5	10.0) 30	.00
	10.00 X	1.50							
					Total	5	10.0) 30	.00
KEY TO H	EAT								
Heat Cod	e :	Heat No.							
048250		543865							
TEST RES	ULTS								
Chemical	compos	ition (wei	ght%)						
Heat	C	Si	Mn	Р		S	Cr	Ni	Mo
048250	0.017	0.39	1.63	0.0	32	0.0100	17.23	13.05	2.52
	N								
048250	0.036								
Chemical composition, product (weight%)									
Heat	C	Si	Mn	P		S	Cr	Ni	Мо
048250	0.017	0.40	1.63	0.0	34	0.0100	-	13.08	2.53
	N								
048250	0.035								
Quality assurance – Lars-Åke Bergqvist / QA-manager									
-	-		TC Serv				-		
				-		1 (020 1			160001

AB SANDVIK MATERIALS TECHNOLOGY Reg No. 556234-6832 VAT No. SE663000-060901 SE-81181 SANDVIKEN SWEDEN www.smt.sandvik.com mtc_service.smt@sandvik.com



· · · · · · · · · · · · · · · · · · ·						
Tensile test		temperature strength	Tensile strength	Elongation		
	MPA	MPa	MPa	% %		
Lot		Rp1.0	Rm	A 4D		
57382	331		567	51 48		
Hardness test						
	Min	Max				
Lot	HRB	HRB				
57382	75	76				
<pre>Following controls/tests have been satisfactorily performed: - Flattening test Flaring test - PMI-test Intergranular corrosion test acc to ASTM A-262 PR.E - Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016 Visual inspection and dimensional control.</pre>						
Heat Treatment: Solution annealed at a temperature of Min 1040° C and quenched.						
Marking: SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 10.00 X 1.50 MM HT 543865 SS LOT 57382 MADE BY SANDV IK IN SWEDEN *QA-TUBE*						
The raw material is free from radioactive contamination.						
Material free from mercury contamination.						
Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.						
The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.						
The delivered products comply with the specifications and requirements of the order.						
The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.						
No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.						
The certificate is produced with EDP and valid without signature.						