



**CERTIFICATE**

**No. A/16-582551 Rev 00**  
**Date 2016-06-01 Page 1/2**

INSPECTION CERTIFICATE acc to  
EN 10204 3.1

Processkontroll Items AB  
Box 2088  
444 02 STORA HÖGA  
SWEDEN

INSPECTION STAMP  
QA-TUBE

<b>Customer References</b>		<b>Sandvik References</b>	
753466	Customer order 2016-05-25	Order No. 442686	Subs No. 610711
003-00991	ITEMS	ABSMT No. 300-47310	ABSMT Dispatch note 22352/54 C.Code 15

<b>Material description</b> SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	<b>Steel/material Designations</b> Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
<b>Steel making process</b> Electric furnace	

**Technical requirements**  
 ASTM A-213-15C AW, ASME SA-213-ED-15 AW, ASTM A-269-15A  
 NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17495:2015  
 PED 97/23/EC EN 10216-5 TC1  
 HRB MAX 80

<b>EXTENT OF DELIVERY</b>								
<b>It</b>	<b>Product designation</b>	<b>Heat</b>	<b>Lot</b>	<b>Pieces</b>	<b>Kg</b>	<b>M</b>		
01	THT-3R60-6-1 6.00 X 1.00	048242	56196	80	60.0	480.00		
				<b>Total</b>	80	60.0	480.00	
<b>KEY TO HEAT</b>								
<b>Heat Code</b>	<b>Heat No.</b>							
048242	544140							
<b>TEST RESULTS</b>								
<b>Chemical composition (weight%)</b>								
<b>Heat</b>	<b>C</b>	<b>Si</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Cr</b>	<b>Ni</b>	<b>Mo</b>
048242	0.021	0.39	1.59	0.030	0.0090	17.28	13.05	2.53
	<b>N</b>							
048242	0.041							
<b>Chemical composition, product (weight%)</b>								
<b>Heat</b>	<b>C</b>	<b>Si</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Cr</b>	<b>Ni</b>	<b>Mo</b>
048242	0.023	0.40	1.61	0.031	0.0080	17.28	13.02	2.51
	<b>N</b>							
048242	0.041							

**Quality assurance - Lars-Åke Bergqvist / QA-manager**  
**MTC Service / Certificates**

**Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	4D
56196	332	376	577	50	49

**Hardness test**

Lot	Min	Max
	HRB	HRB
56196	75	76

**Following controls/tests have been satisfactorily performed:**

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

**Heat Treatment:**

Solution annealed at a temperature of Min 1040° C and quenched.

**Marking:**

SANDVIK 3R60 ASTM/ASME A/SA-213 A-269 EN 10216-5 TC1 EN 10305-1 COLD AW EN 1.4 435 TP316/316L CFA SMLS NDE 6.00 X 1.00 MM HT 544140 SS LOT 56196 MADE BY SANDVIK IN SWEDEN \*QA-TUBE\*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (97/23/EC) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.