

**CERTIFICATE****No. A/17-630308****Rev 00****Date 2017-01-16****Page 1/3**INSPECTION CERTIFICATE acc to
EN 10204 3.1Processkontroll Items AB
Box 2088
444 02 STORA H@GA
SWEDENINSPECTION STAMP
QA-TUBE

Customer References		Sandvik References		
754246	Customer order 2016-12-15	Order No. 463692	Subs No. 621524	ABSMT Dispatch note 36796/54
003-00991	ITEMS	ABSMT No. 300-56384	C.Code 15	

Material description	Steel/material Designations
SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Sandvik SS 3R60 2353/2343 AISI EN no TP316/TP316L 1.4435
Steel making process Electric furnace	

Technical requirements
ASTM A-213-15C AW, ASME SA-213-ED-15 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17495:2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80, SS219713 Condition NO -24

EXTENT OF DELIVERY								
It	Product designation	Heat	Lot	Pieces	Kg	M		
02	THT-3R60-12-1.5 12.00 X 1.50	048305	18467	15	37.0	90.00		
				Total	15	37.0	90.00	
KEY TO HEAT								
Heat Code	Heat No.							
048305	545763							
TEST RESULTS								
Chemical composition (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048305	0.020	0.38	1.51	0.032	0.0100	17.39	13.20	2.71
	N							
048305	0.036							

Quality assurance - Lars-Åke Bergqvist / QA-manager
MTC Service / Certificates

**Chemical composition, product (weight%)**

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048305	0.020	0.38	1.52	0.032	0.0100	17.31	13.25	2.73
	N							
048305	0.032							

Tensile test at room temperature

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
18467	285	316	573	59	57

Hardness test

Lot	Min	Max
	HRB	HRB
18467	74	76

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and ISO 3651-2 A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 12.00 X 1.50 MM HT 545763 SS LOT 18467 MADE IN SWEDEN *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.



No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.