

INSPECTION CERTIFICATE acc to EN 10204 3.1

Processkontroll Items AB Box 2088 444 02 STORA H@GA SWEDEN

INSPECTION STAMP QA-TUBE

Customer References	Sandvik References				
754076 003-00991 ITEMS	Customer order 2016-11-04		Subs No. 619147 C.Code	ABSMT Dispatch note 32406/54	
Material description	Steel/material Designations				
SEAMLESS STAINLESS COLD	FINISHED	Sandvik		AISI	
HYDRAULIC TUBING		3R60		TP316/TP316L	
		EN no			
		1.4435			
Steel making process					
Electric furnace					
Technical requirements					

ASTM A-213-15C AW, ASME SA-213-ED-15 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17495:2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT O	EXTENT OF DELIVERY								
It		et designat	ion	Heat		Pieces	-		-
		50-12-1.5		048307	16659	8	19.0	48.	00
	12.00 >	x 1.50							
					Total	8	19.0	48.	00
KEY TO H	EAT								
Heat Cod 048307	e	<b>Heat No.</b> 545888							
TEST RES	-	, .							
		sition (wei		_		-	-		
Heat		<b>si</b> 0.39	<b>Mn</b>	P		<b>S</b>	<b>Cr</b> 17.23	<b>Ni</b> 13.07	<b>Mo</b> 2.63
040307	0.018 N	0.39	1.00	0.0.	5 L	0.0100	17.25	13.07	2.03
048307	0.036								
Chemical composition, product (weight%)									
Heat	C	Si	Mn	Р		S	Cr	Ni	Mo
048307	0.018	0.40	1.59	0.0	30	0.0090	17.28	13.03	2.62
	N								
048307	0.035								
Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates									

AB SANDVIK MATERIALS TECHNOLOGY Reg No. 556234-6832 VAT No. SE663000-060901 SE-81181 SANDVIKEN SWEDEN www.smt.sandvik.com mtc\_service.smt@sandvik.com



Tensile test	Yield s	trength	Tensile strength	-		
Lot	MPA Rp0.2	MPa Bp1 0	MPa Rm	%% A 2"		
16659		346	582	<b>A 2</b> <sup></sup> 49 48		
Hardness test						
	Min	Max				
<b>Lot</b> 16659	<b>HRB</b> 76	<b>HRB</b> 78				
	test.		n satisfactorily pe	rformed:		
- PMI-test.						
<ul> <li>- Intergranular corrosion test acc to ASTM A-262 PR.E</li> <li>- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.</li> <li>- Visual inspection and dimensional control.</li> </ul>						
Heat Treatment: Solution annealed at a temperature of Min 1040° C and quenched.						
Marking: SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 12.00 X 1.50 MM HT 545888 SS LOT 16659 MADE IN SWEDE N *QA-TUBE*						
The raw material is free from radioactive contamination.						
Material free from mercury contamination.						
No welding or weld repair.						
Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU) by TUEV NORD; notified body, reg.no. 0045.						
The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.						
The delivered products comply with the specifications and requirements of the order.						
The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.						
No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.						
The certificate is produced with EDP and valid without signature.						

AB SANDVIK MATERIALS TECHNOLOGY Reg No. 556234-6832 VAT No. SE663000-060901 SE-81181 SANDVIKEN SWEDEN www.smt.sandvik.com mtc\_service.smt@sandvik.com