



CERTIFICATE

No. A/18-738105

Rev 00

Date 2018-04-24

Page 1/3

INSPECTION CERTIFICATE acc to
EN 10204 3.1

Processkontroll Items AB
Box 2088
444 02 STORA H@GA
SWEDEN

INSPECTION STAMP
QA-TUBE

Customer References		Sandvik References	
756330	Customer order 2018-04-20	Order No. 511569	Subs No. 650212
003-00991	ITEMS	ABSMT No. 300-79979	C.Code 15
		ABSMT Dispatch note 20059/54	

Material description SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Steel/material Designations Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
Steel making process Electric furnace	

Technical requirements
 ASTM A-213-17 AW, ASME SA-213-ED-17 AW, ASTM A-269-15A
 NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17945:2015
 PED 2014/68/EU EN 10216-5 TC1
 HRB MAX 80

EXTENT OF DELIVERY

It	Product designation	Heat	Lot	Pieces	Kg	M
01	THT-3R60-12-1	551672	39952	109	184.0	654.00
	12.00 X 1.00	551672	39953	26	44.0	156.00
				Total	135	228.0
						810.00

TEST RESULTS

Chemical composition (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
551672	0.019	0.43	1.63	0.027	0.009	17.29	13.07	2.62
	N							
551672	0.048							

Chemical composition, product (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
551672	0.022	0.44	1.64	0.028	0.008	17.30	13.09	2.64
	N							
551672	0.050							

Quality assurance - Sofia Åkesson / Q-Manager
MTC Service / Certificates

**Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
39952	347	390	610	46	42
39953	349	393	618	45	41

Hardness test

Lot	Min	Max
	HRB	HRB
39952	77	78
39953	75	77

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 12.00 X 1.00 MM HT 551672 SS LOT 39952 MADE IN SWEDEN *QA-TUBE*

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 12.00 X 1.00 MM HT 551672 SS LOT 39953 MADE IN SWEDEN *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.



No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.