



CERTIFICATE

A03/Z02

No. A/20-865336 Rev 00

Date 2020-01-03 Page 1/3

A02/Z03

INSPECTION CERTIFICATE acc to EN 10204 3.1

A06

PROCESSKONTROLL ITEMS AB BOX 2088 444 02 STORA HÖGA SWEDEN

INSPECTION STAMP QA-TUBE

Customer References A07	Sandvik References A08
Customer order 2019-12-18	Order No. Subs No. ABSMT Dispatch note 547036 678742 10402/54
758921	ABSMT No. C.Code 300-14886 15
003-00991 ITEMS	

Material description B01/B04	Steel/material Designations B02
SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Sandvik AISI 3R60 TP316/TP316L
	EN no 1.4435
Steel making process Electric furnace	
C70	

Technical requirements B03
ASTM A-213-18B AW, ASME SA-213-ED-17 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:-2015, NACE MR0103/ISO 17945-1:-2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY							B07-B13
It	Product designation	Heat	Lot	Pieces	Kg	M	
03	THT-3R60-28-2 28.00 X 2.00	556541	18750	2	15.0	12.00	
				Total	2	15.0 12.00	
TEST RESULTS							
Chemical composition (weight%)							
Heat	C	Si	Mn	P	S	Cr Ni Mo	
556541	0.020	0.39	1.64	0.033	0.008	17.29 13.13 2.63	
	Co	N					
556541	0.10	0.039					
Chemical composition, product (weight%)							
Lot	C	Si	Mn	P	S	Cr Ni Mo	
18750	0.018	0.39	1.63	0.034	0.008	17.33 13.12 2.63	
	N						
18750	0.039						

Quality assurance - Sofia Åkesson / Q-Manager MTC Service / Certificates	A05/Z02
------------------------------------------------------------------------------------	---------



**Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPA	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
18750	285	320	581	57	62
	293	327	592	52	56

Hardness test

Lot	Min	Max
	HRB	HRB
18750	76	78

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 AW EN 1.4435 TP316/3 16L CFA SML NDE 28.00 X 2.00 MM HT 556541 SS LOT 18750 MADE IN SWEDEN *QA-TUBE *

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2015.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.





The certificate is produced with EDP and valid without signature.

