



CERTIFICATE

A03/Z02

No. A/20-912168

Rev 00

Date

2020-09-23

Page

1/3

A02/Z03

INSPECTION CERTIFICATE acc to EN 10204 3.1

A06

PROCESSKONTROLL ITEMS AB BOX 2088 444 02 STORA HÖGA SWEDEN

INSPECTION STAMP

QA-TUBE

Customer References A07 759972 003-00991 ITEMS <div style="text-align: right;"> Customer order 2020-09-11 </div>	Sandvik References A08 <table border="0" style="width: 100%;"> <tr> <td>Order No.</td> <td>Subs No.</td> <td>ABSMT</td> <td>Dispatch note</td> </tr> <tr> <td>559158</td> <td>688571</td> <td>25095/54</td> <td></td> </tr> <tr> <td>ABSMT No.</td> <td>C.Code</td> <td colspan="2"></td> </tr> <tr> <td>300-23738</td> <td>15</td> <td colspan="2"></td> </tr> </table>	Order No.	Subs No.	ABSMT	Dispatch note	559158	688571	25095/54		ABSMT No.	C.Code			300-23738	15		
Order No.	Subs No.	ABSMT	Dispatch note														
559158	688571	25095/54															
ABSMT No.	C.Code																
300-23738	15																

Material description B01/B04 SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING Metallurgical process C70 Electric furnace	Steel/material Designations B02 <table border="0" style="width: 100%;"> <tr> <td>Sandvik</td> <td>AISI</td> </tr> <tr> <td>3R60</td> <td>TP316/TP316L</td> </tr> <tr> <td>EN no</td> <td></td> </tr> <tr> <td>1.4435</td> <td></td> </tr> </table>	Sandvik	AISI	3R60	TP316/TP316L	EN no		1.4435	
Sandvik	AISI								
3R60	TP316/TP316L								
EN no									
1.4435									

Technical requirements B03 ASTM A-213-19 AW, ASME SA-213-ED-19 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:-2015, NACE MR0103/ISO 17945-1:-2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY B07-B13								
It	Product designation	Heat	Lot	Pieces	Kg	M		
	02 THT-3R60-28-1.5 28.00 X 1.50	559737	30192	6	35.0	36.00		
				Total	6	35.0 36.00		
TEST RESULTS								
Chemical composition (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
559737	0.017	0.45	1.61	0.035	0.008	17.43	13.15	2.63
	Co	N						
559737	0.12	0.042						
Chemical composition, product (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
559737	0.020	0.46	1.61	0.035	0.005	17.44	13.14	2.64
	N							
559737	0.044							

Quality assurance - Sofia Åkesson / Q-Manager MTC Service / Certificates	A05/Z02
--	---------

A01



**Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
30192	256	296	574	61	63
	266	307	584	56	53

Hardness test

Lot	Min	Max
	HRB	HRB
30192	70	73

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 AW EN 1.4435 TP316/3 16L CFA SML NDE 28.00 X 1.50 MM HT 559737 SS LOT 30192 MADE IN SWEDEN *QA-TUBE *

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2015.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.





The certificate is produced with EDP and valid without signature.

