



**Chemical composition, product (weight%)**

Lot	C	Si	Mn	P	S	Cr	Ni	Mo
94198	0.015	0.40	1.67	0.028	0.007	17.36	12.82	2.58
	N							
94198	0.042							

**Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
94198	254	291	583	53	57
	250	287	574	54	57

**Hardness test**

Lot	Min	Max
	HRB	HRB
94198	72	72

**Following controls/tests have been satisfactorily performed:**

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

**Heat Treatment:**

Solution annealed at a temperature of Min 1040° C and quenched.

**Marking:**

SANDVIK 3R60 ASTM/ASME A/SA213 A269 COLD EN 10216-5 TC1 AW TP 316/TP 316L EN 1.4435 CFA SML 20.00 X 2.00 MM . HT 562555 SZ LOT 2039871-11 MADE BY SANDVIK IN CZECHIA \*QA-TUBE\*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2015.





No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.

TEST RESULTS TRANSFERRED FROM CERTIFICATE NO C-2838/40

