



CERTIFICATE

A03/Z02

No. A/22-104921

Rev 00

Date

2022-04-12

Page

1/3

A02/Z03

INSPECTION CERTIFICATE acc to
EN 10204 3.1

A06

PROCESSKONTROLL ITEMS AB
BOX 2088
444 02 STORA HÖGA
SWEDEN

INSPECTION STAMP

QA-TUBE

Customer References A07 762091 Customer order 2022-01-14 003-00991 ITEMS -W	Sandvik References A08 Order No. Subs No. SMT Dispatch note 580864 706495 11915/54 SMT No. C.Code 300-39695 15
---	--

Material description B01/B04 SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING Metallurgical process C70 Electric furnace	Steel/material Designations B02 Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
---	---

Technical requirements B03 ASTM A-213-19 AW, ASME SA-213-ED-19 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:-2015, NACE MR0103/ISO 17945-1:-2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY B07-B13						
It	Product designation	Heat	Lot	Pieces	Kg	M
	02 THT-3R60-25-2 25.00 X 2.00	042673	95185	6	42.0	36.00
				Total	6	42.0 36.00
KEY TO HEAT			KEY TO LOT			
Heat Code	Heat No.			Lot Code	Lot No.	
042673	564421			95185	2054608-11	
TEST RESULTS						
Chemical composition (weight%)						
Heat	C	Si	Mn	P	S	Cr Ni Mo
042673	0.019	0.42	1.64	0.031	0.009	17.26 13.04 2.62
	N					
042673	0.045					

Quality assurance - Sofia Åkesson / Q-Manager MTC Service / Certificates	A05/Z02
--	---------



**Chemical composition, product (weight%)**

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
042673	0.018	0.43	1.64	0.031	0.006	17.34	13.04	2.61
	N							
042673	0.049							

Tensile test at room temperature

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
95185	253	288	583	51	56
	260	295	591	51	56

Hardness test

Lot	Min	Max
	HRB	HRB
95185	74	75

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM/ASME A/SA213 A269 COLD EN 10216-5 TC1 AW TP 316/TP 316L EN 1.4435 CFA SML 25.00 X 2.00 MM . HT 564421 SZ LOT 2054608-11 MADE BY SANDVIK IN CZECHIA *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2015.





No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.

TEST RESULTS TRANSFERRED FROM CERTIFICATE NO C-3329/10

