

Chemical composition, product (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
044337	0.020	0.37	1.63	0.030	0.007	17.16	13.02	2.6
	N							
044337	0.040							

Tensile test at room temperature

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
96381	340	364	588	69	53
96387	340	365	587	63	52

Hardness test

Lot	Min	Max
	HRB	HRB
96381	73	75
96387	75	76

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

3R60 ASTM/ASME A/SA213 A269 COLD EN 10216-5 TC1 AW TP 316/TP 316L EN 1.4435 CF
 A SML NDE 6.35 X 0.89 MM 1/4'' X 20 BWG/SWG HT 566000 SZ LOT 2078285-11 MADE B
 Y ALLEIMA IN CZECHIA *QA-TUBE*

3R60 ASTM/ASME A/SA213 A269 COLD EN 10216-5 TC1 AW TP 316/TP 316L EN 1.4435 CF
 A SML NDE 6.35 X 0.89 MM 1/4'' X 20 BWG/SWG HT 566000 SZ LOT 2078256-11 MADE B
 Y ALLEIMA IN CZECHIA *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2015.



No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of Alleima.

Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.

Alleima, formerly Sandvik Materials Technology. During a brand transition period, both Sandvik and Alleima marking on products may exist.

TEST RESULTS TRANSFERRED FROM CERTIFICATE NO C-7131/40
C-7131/40

